

POLISHING ANTIFOULING

Silver Cruise



Technical information

Product components :	Silver Cruise Polishing Antifouling – one pack product
Volume:	Single pack : 0,75 l, 2,5 l
Product description :	Silver Cruise Polishing Antifouling it's effectively preventing fouling organism: aquatic plants and animals or slime. Ideal paint for professional and consumer application on salt and fresh water.
Recommended use :	This antifouling is recommended to use on sailboats or powerboats up to 30 knots of speed. Easy application, no need to sand between coats, increased speed and efficiently. Silver Cruise Polishing Antifouling Sea-Line® can be applied on hulls made of : - laminate - steel - wooden

Do not use on aluminum or zinc surfaces.

Use biocides safely. Always read the label and product information before use.

Physiochemical Characteristics:

Color:	White, Red, Blue, Navy, Black
Gloss:	matte
Solid parst:	51 %
VOC (as supplied):	427 g/l average
VOC (EU Solvent):	286 g/kg average EU Solvent Emissions Directive (Council Directive 1999/13/EC) 9 ~ 10 m ² /dm ³ (by roller) 3 ~ 5 m ² /dm ³ (by spray)
Theoretical yielded:	98 µm (by roller) 196 µm (by spray)
Coat thickness (WFT):	50 µm (by roller) 100 µm (by spray)
Finish thickness (DFT):	

NOTICE: Exposure of a freshly applied antifouling paint to moist air can lead to color change.
The discoloration is only superficial and does not affect the effectiveness of the antifouling paint.

Due to the content of copper oxide, a small color difference between the parts of the antifouling paint is acceptable.

Preparing the surface: Check is Silver Cruise Polishing Antifouling Sea-Line® compatible with previous antifouling on your boat. Do not use on antifouling with PTFE.

Surface must be clean, dry and temperature of it should be higher than dew point to avoid condensation. High relative humidity or condensation within the first 24 hours after the application, may adversely affect formation of coating. Remove salt and other contaminants with pressurized fresh water. Sand laminate surfaces to uniform roughness (the sand paper of gradation P80-P120)

As a pre-coat, it is recommended to use:

- 2K Epoxy Lightprimer 5:1 Sea-Line® - laminate (GFK)
- 2K Epoxy Anticorrosive 4:1 Sea-Line® - steel
- 2K Epoxy Woodprimer 10:4 Sea-Line® - wood
- 1K UNIVERSAL PRIMER Sea-Line® - laminate, steel, wood

Metod of application: roller, brush, airless spray gun (professional only)

Recommended number of coats 1 ÷ 2 layers

Thickness of dry layer is: 100 µm (DTF)

On places where growth of lichens is the largest (water line) and on places exposed to damage (keel, prow etc.) is recommend to apply extra coat antifouling paint.

Minimum application temperature: +5°C.

POLISHING ANTIFOULING

Silver Cruise



Technical information

Airless spraying parameters:

Airless spray

- Apply 1 coat of 196 µm of the dry layer
- Tip size : 517 - 521
- Working pressure : 176-220 bar / 2500-3200 psi

Thinner:

Not recommended

NOTICE:

In the case of high temperatures and the need to thin the antifouling paint, a maximum dilution of 0-5% (by volume) is recommended.

Dilution and the application method directly affect the thickness of the antifouling paint layer.

Special attention should be paid to obtaining a specific coating thickness (100 µm DTF), which ensures the effective operation of the antifouling paint.

Hardening the surface:

Touch Dry:

23°C

15°C

5°C

30 minutes

45 minutes

1 hour

Dry to recoat (overcoated):

Min 6 hours

Min 10 hours

Min 16 hours

Dry to launch

(immersion times):

Min 4 hours

Min 6 hours

Min 8 hours

Max 6 months

Max 6 months

Max 6 months

The given times must be considered as guidelines only. The actual drying time may be longer or shorter and depends on film thickness, ventilation, humidity, etc

Further Work :

Maximum immersion time after application Silver Cruise polishing antifouling is 6 months.

If launching is between 6 and 12 month after application, before sand surface using sand paper P220. Launching over 12 month after application, surface should be sanded and one more time painted.

HSE conditions :

Please follow safety instructions from the technical data sheet for hazardous chemical and follow workplace safety laws. The general rule is to avoid contact with skin and eyes. When using the product in a small, enclosed space you must provide forced ventilation. It is also recommended that you protect your respiratory system, eyes, and skin. Be particularly careful of fire as the product may explode.

Storage :



Product components should be kept in tightly sealed containers, at a temperature between 5-35°C, away from sources of fire, heat, and sun rays.

Close the containers tightly immediately after every use

Expiration date:



2 years from the date of production

Quality Guarantee :

Production, quality control, and the realization of deliveries fulfill the demands of ISO 9001 and 14001 standards.

All data in this document have been prepared for informational purposes. We can not take responsibility for the results of user actions over which we have no control. Responsibility of the user is to make the test sample and determine the suitability of the product for individual applications. Sea-Line do not take responsibility for any damages, or loss of profits associated with the improper use of the products.

All information is based on scrupulous laboratory research and many years of experience. Our position of market leadership does not free us from constant quality control of our products. However, we do not accept responsibility for the effects of improper use or storage of our products, or for the effects of using our products in any way contrary to the standards of good workmanship.