SEAGUARD bottom paint

Technical Information



Product Description:	Biocide free, solvent paint recommended to protect areas below the water line. The coating offers very easy to apply conditions and short drying time.
Volume:	Single pack 0,75 I. and 2,5 I
Uses	Suitable for all kind of boats up to 30 knots of speed. It can be applied on steel, aluminium, wood or fiberglass hulls. Recommended for lakes.
Physiochemical Characte- ristics	
Color: Gloss Solid parts: Theoretical yield: Coat thickness (WFT):	blue, white, black semi gloss 51-52 % (depend on color) 9 - 10 m ² /dm ³ for tickness (DTS) 50 μm 100 μm

Surface preparation

Density:

Finish thickness (DFT):

1,41 kg/l Coated surfaces

50 µm

Prior to paint application, all surfaces should be clean, dry and free from contamination. Remove surface contamination by high pressure fresh water cleaning. To be applied on a clean, dry approved sea-Line epoxy primer (Epoxy Anticorrosive Sea-Line[®] or Epoxy Lightprimer Sea-Line[®]), 1K universal primer / or intact, compatible self-polishing antifouling.

Other surfaces

The coating may be used on other substrates. Please contact info@sea-line.eu

Application: Brush/ Roll Paint brush / roller - care must be taken to achieve the specified dry film thickness. Apply 2 layers.

Application Spray gun application:

Air spray application (90÷100 μm wet) Gravity Fed: 1,4÷1,6mm, Working pressure : 3,0 bar Apply 2 layers



	20°C	10°C
Touch Dry:	2 hours	3 hours
Through dry:	10 hours	16 hours
Dry to recoat	Min 8h - max 7days	Min 16h - max 7 days
Dry to launch:	Min 12 hours – max 30 days	24 hours – max 30 days

SEAGUARD bottom paint

Technical Information



	The given times must be considered as guidelines only. The actual dry- ing time may be shorter or longer and depends on film thickness, ventila- tion, humidity, underlying paint system etc. A complete system can be described on a system sheet, where all parameters and special condi- tions could be included.
CAUTION	Exposure of freshly applied antifouling paint to wet contact air may change color. Discoloration is only superficial and does not affect the effectiveness of antifouling paint.
	After immersion, it shows a slight change in color.
General Cautions	
	 Minimum application temperature: +5 °C. It is necessary to use personal protective gear when using this product. Protect the respiratory system, skin, and eyes. Ventilate the work space. Clean tools immediately after application.
	Caution: In the interest of safety, always act in accordance with the data in the technical data sheet.
Storage	Product contents should be kept in tightly sealed containers, in a cool, dry location, away from open flames, heat, and sunlight.
Expiration	Caution: After every use, containers should be closed immediately! Pro- tect hardener from overheating! 36 months from date of production.
Quality Guarantee	Production, quality control, and the realization of deliveries fulfill the de- mands of ISO standards 9001 and 14001

SEAGUARD bottom paint

Technical Information



All data in this document have been prepared for informational purposes. We can not take responsibility for the results of user actions over which we have no control. Responsibility of the user is to make the test sample and determine the suitability of the product for individual applications.Sea-Line do not take responsibility for any damages, or loss of profits associated with the improper use of the products.

All information is based on scrupulous laboratory research and many years of experience. Our position of market leadership does not free us from constant quality control of our products. However, we do not accept responsibility for the effects of improper use or storage of our products, or for the effects of using our products in any way contrary to the standards of good workmanship.

TROTON sp. z o.o. Ząbrowo.