

Technical Data Sheet

SILVER CRUISE POLISHING ANTIFOULING



PRODUCT DESCRIPTION

One component paint for protection hulls against fouling.

Silver Cruise Polishing Antifouling it's effectively preventing fouling organism: aquatic plants and animals or slime. Ideal paint for professional and consumer application on salt and fresh water. This antifouling is recommended to use on sailboats or powerboats up to 30 knots of speed. Easy application, no need to sand between coats, increased speed and efficiently. **Do not use on aluminum or zinc surfaces. Use biocides safely. Always read the label and product information before use.**

PRODUCT INFORMATION

SURFACE TYPE	Laminate, wood, steel
COLOUR	White, red, blue, navy blue, black
GLOSS	mate
VOLUME SOLIDS	51 %
VOC (as supplied)	427 g/l average
VOC (EU solvent)	286 g/kg average EU Solvent Emissions Directive (Council Directive 1999/13/EC)
MIXING RATIO	Not applicable
THEORETICAL COVERAGE	9-10m ² /l per coat (by roller) , 3-5m ² /l per coat (by spray) ,
METHOD OF APPLICATION	brush/roll spray airless– professional use only

INSTRUCTION FOR USE

SURFACE PREPARATION	<p>NEW BOATS without previous antifouling coats and other fouling protection, if on boats doesn't exist any antifouling coats or paint coats it is recommended to use as a precoat:</p> <p>Laminate –osmosis protection, epoxy Lightprimer or epoxy primer HS, details on TDS for primers</p> <p>Steel- anticorrosion protection, epoxy primer Anticorrosion, details on TDS for primers</p> <p>Wood- protection against water, epoxy Lightprimer, details on TDS for primers</p> <p>EXISTING ANTIFOULING PROTECTION, in this case first we should check compatibility between exiting antifouling coats and new antifouling paint. Check Sea-Line compatibility table on www.sea-line.eu or info@sea-line.eu</p> <p>Existing antifouling in poor condition or old antifouling is not compatible, remove all old antifouling layers by sanding on wet and follow to instruction for new boats without previous layers.</p> <p>Existing antifouling in good condition and compatible before application of new layers, sand surface on wet using sand paper P120-P240. After sanding clean and degrease surface by Sea-Line Cleaner.</p> <p>Existing antifouling in good condition and unknown type (except paints which includes Teflon) is recommended to sand surface on wet using sand paper P120-P240. Then use as a barrier layer Sea-Line Universal Primer 1K – see TDS for this product.</p> <p>Instructions for preparing surfaces and primers before applying anti-fouling paints are provided on the TDS for the specific primer.</p>
PRODUCT PREPARATION	This paint is one pack product. Always mix thoroughly paint in can, before use.
THINNING	<p>NOT RECOMMENDED</p> <p>Only in exceptional circumstances like high temperature, maximum permissible level is 5% by volume. For thinning use Sea-Line Antifouling Thinner. Dilution has a direct effect on the thickness of the antifouling paint coating.</p>

Technical Data Sheet

SILVER CRUISE POLISHING ANTIFOULING



APPLICATION	Number of coats	1-2 layers (total DFT of 100 microns) 50 microns DFT/98 WFT per coat by brush/roller 100 microns DFT/196 WFT per coat by spray On places where growth of lichens is highest (water line) and on places exposed to damage (keel, prow etc.) is recommend to apply extra coat of antifouling paint.
-------------	-----------------	--

Airless spray parameters	Thick layer of airless spray application (196 µm DFT)
Tip size	517-521
pressure	176-220 bar/2500-3200 psi

CURING INFORMATION

Temperature	Overcoating interval	Dust dry	Dry to launch
23°C	Min 6 h	30 min.	Min 4 h Max 6 months
15°C	Min 10 h	45 min.	Min 6 h Max 6 months
5°C	Min 16 h	1 h	Min 8 h Max 6 months

The given times must be considered as a guideline only. The actual drying time may be longer or shorter depending on film thickness, ventilation, humidity etc.

IMPORTANT NOTES

Minimum application temperature is +5°C
High humidity level or condensation within the first 24 hours after application, may adversely affect formation of coating.
Exposure of fresh painted surface to moist air can lead to color change. The discoloration is only superficial and does not affect the effectiveness of the antifouling paint.
After launching can be visible slightly color differences.
Due to the content of copper oxide, a small color difference between the parts of the antifouling paint is acceptable.

It is important to achieve specified film thickness which will provide effective work of antifouling paint. Reduction of layer thickness will affect directly on effectiveness.

Maximum immersion time after application antifouling SILVER CRUISE is 6 months. If launching is between 6 and 12 months after application, sand surface using abrasive paper P220 before launching. Launching over 12 months after application, surface should be sanded and painted again.

STORAGE AND SAFETY INFORMATION

SHELF LIFE	24 months from production date
STORAGE	Product components should be stored in tightly sealed containers, in a temperature of 10-25°C, away from sources of fire, heat and sunlight. Close container tightly immediately after each use. Store in a dry place and keep sealed cans until use.
HSE CONDITIONS	Please follow safety instructions from the Safety Data Sheet for hazardous chemical and

Technical Data Sheet

SILVER CRUISE POLISHING ANTIFOULING



follow workplace safety laws. The general rule is to avoid contact of the product with the skin and eyes. When product is used in a small, closed spaces you must provide forced ventilation. It is also recommended that you protect your respiratory system, eyes, and skin. Special care should be taken in the area of fire protection and explosion hazards. **Notice ! Always follow all precautionary, health and safety notice on the Safety Data Sheet and container labels.**

DISCLAIMER

All data in this document have been prepared for informational purpose only. We can not take responsibility for the results of user actions over which we have no control. The user is responsible for making the control sample and determining the suitability of the product for specific, individual applications. Company Troton Sp. z o.o. does not take responsibility for any damage, or loss of profits associated with the improper use of the products. All information is based on scrupulous laboratory research and many years of experience. Our position of market leadership does not free us from constant quality control of our products. However, we do not accept responsibility for the effects of improper use or storage of our products, or the effects of using our products in any way contrary to the standard of good workmanship.

QUALITY GUARANTEE

Production, quality control and the realization of deliveries fulfill the demands of ISO 9001 and 14001 standards.